

## Temalac SC-F 40

**DESCRIPTION** A high solids alkyd paint, containing anti-corrosive pigments.

### PRODUCT FEATURES

**RECOMMENDED USES** Recommended for steel framework, service platforms and different types of machinery and equipment.

### TECHNICAL DATA

**Features** Recommended as a single coat system for steel surfaces both indoors and outdoors. Good application properties. High film build.

**Colour Cards** RAL, NCS, SSG, BS, MONICOLOR NOVA ja SYMPHONY värikartat. Tuote kuuluu TEMASPEED -sävytysjärjestelmään.

**Gloss groups** Semi-gloss

**Coverage**

Recommended film thicknesses		Theoretical coverage
dry	wet	
100 µm	160 µm	6,3 m <sup>2</sup> /l
120 µm	200 µm	5,0 m <sup>2</sup> /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

**Thinner** 1006

**Application method** By airless or conventional spray.

**Drying times**

DFT 80 µm	+ 10 °C	+ 23 °C	+ 35 °C
Dust dry, after	30 min	20 min	10 min
Touch dry, after	8 h	5 h	3 h
Recoatable, after	48 h	24 h	16 h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

**Solids volume** 61 ± 2 %. (ISO 3233)  
76 ± 2 %.

**Density** 1.5 kg / l depending on colour.

**Product code** 617-series.

## Temalac SC-F 40

### APPLICATION DETAILS

Application conditions	All surfaces must be dry. The temperature of the ambient air, surface or paint should not fall below + 5 °C during application or drying. Relative humidity should not exceed 80 %. The surface temperature of the steel should remain at least 3 °C above the dew point.
Preparation	Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)  Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1). If blast cleaning is not possible, use phosphating on cold rolled steel.  Primed surfaces: Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)
Priming	TEMALAC SC-F 40
Finishing	TEMALAC SC-F 40
Painting	By airless or conventional spray. Mix the paint thoroughly before use. At airless spray application the paint should be thinned 0 - 5 % and at conventional spray application 5 - 10 %. Airless spray nozzle tip 0.011" - 0.015" and nozzle pressure 160 - 200 bar. Spray angle shall be chosen according to the shape of the object. In order to reach thicker coats use "wet-on-wet" technique.
Cleaning of tools	Thinner 1006.
EU VOC 2004/42/EC-limit value	The Volatile Organic Compounds amount is 360 g/litre of paint. VOC content in ready to use paint (thinned 10 % by volume) is 410 g/l.

### HEALTH AND SAFETY CLASSIFICATION

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oy.