

Temadur SC 50

| | |
|------------------------|---|
| TYPE | A two component semigloss polyurethane paint, containing anticorrosive pigments, hardener aliphatic isocyanate. |
| SUITABILITY | Recommended especially to be used as a single coat finish for agricultural and earth moving machinery and other machinery and equipment. Suitable also to be used as a topcoat in epoxy/polyurethane systems exposed to weathering and chemical stress. |
| EXAMPLES OF USE | Storage tank exteriors, steel framework and other steel structures. |

TECHNICAL DATA

Features Excellent weathering and abrasion resistance. A durable, easy to clean and non-chalking topcoat with good gloss and colour retention.

Colour Cards RAL, NCS, SSG, BS, MONICOLOR NOVA and SYMPHONY colour cards. TEMASPEED tinting.

Gloss groups Semi-gloss

Coverage

| Recommended film thicknesses/one coat application | | Theoretical coverage |
|---|--------|------------------------|
| dry | wet | |
| 80 µm | 125 µm | 8.1 m ² /l |
| 120 µm | 185 µm | 5.4 m ² /l |
| Recommended film thicknesses/as a topcoat | | Theoretical coverage |
| dry | wet | |
| 40 µm | 65 µm | 16.2 m ² /l |
| 60 µm | 95 µm | 10.8 m ² /l |

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

Thinner 1048 and 1067

Mixing ratio Base 5 parts by volume 528-series
Hardener 1 part by volume 008 7640

Application method By airless or conventional spray or by brush.

Pot-life (+23°C) 4 hours

Drying times

| DFT 60 µm | + 5 °C | + 10 °C | + 23 °C | + 35 °C |
|-------------------|-----------------|---------|---------|---------|
| Dust dry, after | 2 h | 1½ h | 50 min | 30 min |
| Touch dry, after | 10 h | 8 h | 6 h | 2 h |
| Recoatible, after | No limitations. | | | |

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

Solids volume 65 ± 2 % volume (ISO 3233)
78 ± 2 % weight

Density 1.4 ± 0.1 kg / l (mixed)

Product code 528-series

INSTRUCTIONS FOR USE

| | |
|-----------------------------------|--|
| Application conditions | All surfaces must be dry. The temperature of the ambient air, surface or paint should not fall below + 5 °C during application or drying. Relative humidity should not exceed 80 %. The surface temperature of the steel should remain at least 3 °C above the dew point. |
| Preparation | <p>Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)</p> <p>Steel surfaces: Blast clean to grade Sa2½. (ISO 8501-1) If blast cleaning is not possible, phosphating is recommended for cold rolled steel to improve adhesion.</p> <p>Zinc surfaces: Sweep blast clean with mineral abrasives, e.g. quartz sand, to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with FONTECLEAN ZN detergent.</p> <p>Hot dip galvanized surfaces are recommended to be painted with a mist coat (paint thinned 25 - 30 %) before the actual priming.</p> <p>Aluminium surfaces: Sweep blast clean with non-metallic abrasives to an even roughness. (SaS, SFS 5873) If sweep blasting is not possible, the surface should be roughened by hand abrading or washed with FONTECLEAN AL detergent.</p> <p>Note! Painted zinc and aluminium surfaces are not recommended when they are exposed to continuous condensation.</p> <p>Primed surfaces: Oil, grease, salt and dirt are removed from the surface by appropriate means. Repair any damage to the primer coat. Note the overcoating time of primer. (ISO 12944-4)</p> |
| Priming | TEMADUR PRIMER, TEMADUR 20, TEMACOAT GPL-S PRIMER, TEMACOAT GF PRIMER, TEMACOAT HB PRIMER, TEMACOAT PM PRIMER, TEMACOAT GPL-S MIO, TEMACOAT RM 40, TEMACOAT SPA MIO, TEMABOND, TEMAPRIME GF, FONTECRYL 10, FONTECRYL AP and FONTECOAT EP PRIMER. |
| Finishing | TEMADUR and TEMATHANE. |
| Painting | By airless or conventional spray or by brush. Depending on the temperature of the components and shape of the object the paint can be thinned 5 - 25 %. Airless spray nozzle tip 0.011" - 0.015" and nozzle pressure 120 - 180 bar. Spray angle shall be chosen according to the shape of the object. In order to reach thicker coats (over 120 µm) use always "wet-in-wet" technique. |
| Mixing of components | First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use Temaspeed Squirrel Mixer for mixing. |
| Cleaning of tools | Thinner 1067 or 1048. |
| EU VOC 2004/42/ EC-limit value | The Volatile Organic Compounds amount is 320 g/litre of paint. VOC content in paint (thinned 25 % by volume) is 440 g/l. |

HEALTH AND SAFETY CLASSIFICATION

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oy.

The above information, based on laboratory tests and practical experience, has been proved valid at the date marked on the product data sheet. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As a manufacturer we cannot be responsible for any damages caused by using the product against our instructions or for inappropriate purposes.

Tikkurila Oy • P.O. Box 53 • Kuninkaalantie 1 • FI-01301 Vantaa Finland • Tel. +358 9 857 71 • Fax. +358 9 8577 6900 VAT FI01970674 • Business Identity Code 0197067-4 • Registered Office Vantaa • e-mail: info@tikkurila.com • www.tikkurila.com