

## Temasil 90

- DESCRIPTION** A two component, ethyl silicate zinc rich paint.
- PRODUCT FEATURES** Can be used as a single coat or as a primer in protective coating systems.
- RECOMMENDED USES** Recommended for bridges, pipework, heat exchangers and chemical tanks etc.

### TECHNICAL DATA

**Features** Offers cathodic protection of steel. Excellent resistance to abrasion and weathering. Excellent resistance also to high, dry temperatures up to + 480 °C. Withstands immersion in oils and various solvents. Separate chemical resistance table available.

**Colour Range** Greenish grey.

**Gloss groups** Matt

**Coverage**

Recommended film thicknesses		Theoretical coverage
dry	wet	
60 µm	120 µm	9.2 m <sup>2</sup> /l
80 µm	160 µm	6.9 m <sup>2</sup> /l

Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated.

**Thinner** 1029

**Mixing ratio** Base 1 part by volume 008 7381  
Hardener 1 part by volume 008 7380

**Application method** By airless or conventional spray or brush.

**Pot-life (+23°C)** 5 hours

**Drying times**

DFT 75 µm	+ 10 °C	+ 23 °C	+ 35 °C
Dust dry, after	½ h	15 min	10 min
Touch dry, after	1 h	½ h	15 min
Recoatable, RH 85 % *see overleaf, after	36 h	5 h	2 h
Recoatable, RH 70 %, after	48 h	24 h	7 h
Recoatable, RH 50 %, after	-	48 h	24 h

Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.

**Solids volume** 55 ± 2 % volume

**Density** 2.0 kg / l (mixed)

**Product code** 008 7381

## Temasil 90

### APPLICATION DETAILS

Application conditions	All surfaces must be dry. The temperature of the ambient air or surface should not fall below -15 °C during application and drying. Relative humidity should be 50 - 90 %. The surface temperature of the steel should remain at least 3 °C above the dew point.
Preparation	Oil, grease, salts and dirt are removed by appropriate means. (ISO 12944-4)
Finishing	Steel surfaces: Blast clean to grade Sa2½ - 3. (ISO 8501-1) Temachlor 40, Temacryl AR, Temacryl EA, Temal, Temacoat GPL-S Primer, Temacoat GPL-S MIO, Temacoat RM 40 and Temacoat SPA.
Painting	Temasil 90 may be overcoated with above mentioned paints when Thinner 1029 does not dissolve the coat. Before overcoating it is recommended to spray a misty coat with 25 % thinned Temacoat GS 50. By airless or conventional spray or brush. Agitate during application. Depending on the application method the paint can be thinned 0 - 5 % by volume. Airless spray nozzle tip 0.018" - 0.021" and nozzle pressure 120 - 180 bar. Spray angle shall be chosen according to the shape of the object.  When coating interiors of chemical tanks or working in dry conditions, it is recommended to rinse the paint film with fresh water 1 - 24 hours after application. Sharp edges, corners, weld seams and other areas difficult to cover properly by spray application should be coated by a brush before the spray application.  Note! There is a risk of mudcracking or peeling with heavier coats than approx. 100 µm dry film thickness.  Separate application instructions available.
Mixing of components	First stir base and hardener separately. The correct proportions of base and hardener must be mixed thoroughly before use. Use Temaspeed Squirrel Mixer for mixing.
Cleaning of tools	Thinner 1029.
EU VOC 2004/42/EC-limit value	The Volatile Organic Compounds amount is 470 g/litre of paint. VOC content of the paint mixture (thinned 5 % by volume) is 480 g/l.

### HEALTH AND SAFETY CLASSIFICATION

Containers are provided with safety labels, which should be observed. Further information about hazardous influences and protection are detailed in individual health and safety data sheets. A health and safety data sheet is available on request from Tikkurila Oy.